



Fornace S.I.L.A. SRL

P.IVA 00216830406
47100 Forli - Via Schiova, 17
Tel. 0543 72.80.75 Fax 0543 72.60.60
www.fornacesila.com
info@fornacesila.com

Cotto Terra Nobile®

SPECIFICATION ITEMS

MASONRY

... cm thick masonry (heads) made of handmade bricks with 5 exposed sand-faced surfaces of the following size (*)..... , (**)..... colour. Bricks

made with a mix of Romagna's alluvial clay moulded in appropriate wooden caissons and left to dry for at least 80 hours and then baked in a Hoffman kiln at a temperature of at least 1030°C.

The masonry must be made using natural hydraulic lime mortar with a low content of soluble salts and joints must be pointed, smoothed and brushed according to the works management's instructions, following the specific indications for a correct laying. The price includes the charges for the removal of mortar residues from the surface and the final washing with a solution of water and duly diluted hydrochloric acid.

Total sqm.....

(*) 12x25x5.5 - 14x28x5.5

(**) light classic sand-faced, rosy classic sand-faced, Romagna's yellow,

Romagna's light pink, antiqued.